

# TECHNICKÝ LIST /

# **AD 501**

# C1 cement adhesive



Standard adhesive for the gluing of ceramic tiles in internal environments.

#### **DECLARATION:**

Standard-setting cement adhesive, type/class C1 according to EN 12004+A1.

#### APPLICATION:

This adhesive is intended for the gluing of highly water-absorbing ceramic tiles (Group Allb, AllI, Bllb and Blll) in bathrooms, kitchens, living rooms, and the like.

Only in internal areas on common bases (plaster, concrete).

#### COMPOSITION:

Aggregates, cement, redispersible polymer, and other additives improving processing and end-use properties of the adhesive.

### **TECHNICAL PARAMETERS:**

MANDATORY						
Use in practice:	Internal installation of tiles on the wall					
Initial tensile adhesion strength			Reaction to fire	Class A1/A1 <sub>fl</sub>		
Tancila adhasian strongth		min. 0.5 MPa	Release of dangerous substances	See the Safety Data Sheet		
Tensile adhesion strength: - after water contact		IIIIII. U.S IVIPA	Withering time (open time): - tensile adhesion strength min. after 20 minutes	min. 0.5 MPa		

INFORMATIVE					
Grain size			0-0.7 mm		
Amount of mixing water:		per 1 kg of dry mixture	0.24-0.28 l/kg		
Amount of mixing water.		per 1 bag (25 kg)	6.0-7.01		
Spreading rate			approx. 1250 kg/m <sup>3</sup>		
Pot life			approx. 2 hours		
		T			
Approximate coverage:	small mosaic up to 50 mm	tooth height of 3-4 mm	approx. 1.6-2.1 kg/m <sup>2</sup>		
	wall tiles 100-250 mm	tooth height of 6-8 mm	approx. 3.1-4.2 kg/m <sup>2</sup>		
	wall tiles over 300 mm	tooth height of 8-12 mm	approx. 4.2-6.3 kg/m <sup>2</sup>		

NOTE: The technical parameters are determined under standard conditions  $(23 \pm 2)^{\circ}$ C and  $(50 \pm 5)\%$  of relative air humidity.

# BASE PREPARATION:

The base must be load-bearing, clean, mature, even, solid, free of dust, grease and other impurities, and should not be frozen. In order to reduce the suction capacity of the base, use **PE 201** or **PE 202** penetration coatings (for instructions for use, refer to the Technical Data Sheet of the used materials). Ceramic tiles can be laid on the bases prepared in this manner after 1 day.

LASSELSBERGER, s.r.o. Adelova 2549/1 320 00 Plzeň - Jižní Předměstí Czech Republic TEL +420 378 021 111 FAX +420 378 021 119 E-MAIL info@rako.cz WEB www.rako.cz BANK DETAILS: Česká spořitelna, a. s. 6221912/0800

Company ID number 25238078 Tax ID number CZ25238078



# TECHNICKÝ LIST /

#### PROCESSING:

Pour the dry mixture evenly into the prescribed amount of water, and mix thoroughly with a high-speed stirrer to produce a smooth, uniform mass. Allow the mixture to stand for approx. 5 minutes, then mix it again shortly. The adhesive is applied on the base using the toothed trowel so that the smoother forms an angle of 60-70° with the base. On the base prepared in this way, tiles are laid and fixed in joints using spacers according to the selected joint width. Tiles are laid only until the time declared as open time. If this time is exceeded, the tiles should not be laid on the applied adhesive (need to be removed). If the tiles are glued on an uneven base, apply the adhesive, using the straight side of the trowel, in a thin layer also on the back side of the tile.

Jointing is carried out after sufficient maturation of the adhesive, after approximately 24-48 hours. The surface may be fully loaded after 7 days.

## Cleaning:

Using a foam trowel, wipe the fresh adhesive off the tiled surface before it hardens, then wash the surface with clean water. Remove the hardened adhesive mechanically. Smaller residues of adhesive can be removed using the **CL 802** special cleaning agent.

#### CAUTION:

- The general rules specified in ČSN 73 3451 should be followed when designing and laying of ceramic tiles.
- . The mixture can be mixed only with drinking water, or water conforming to standard EN 1008.
- It is inadmissible to add additional binders, aggregates, and other additives. Sifting of the mixture is inadmissible too.
- The mixture can be processed only under the air and base temperature over +5 (max. +30°C higher temperatures shorten the open time)!
   The work cannot be done if frost is expected.
- Unused residues should be mixed with water and allow them to harden they can be disposed of as construction wastes; contaminated containers should be disposed
  as of hazardous wastes (see the Safety Data Sheet).
- Only completely emptied and clean packaging may be handed over to recycling

#### FIRST AID, SAFETY AND HYGIENE REGULATIONS:

See the product Safety Data Sheet.

#### STORAGE:

The product should be stored in original containers – protected from damage, action of water, and high relative air humidity. If the storage conditions are met, the shelf life will be 12 months. The expiration date is specified on the packaging.

#### SHIPPING

The dry mixture is supplied in 25 kg paper bags placed on pallets wrapped in foils.

#### QUALITY:

- The product quality is regularly checked in the manufacturer's laboratories.
- The production control system is used in manufacture, and a certified quality management system, according to ISO 9001, is applied.
- Continuous surveillance and proving the conformity of products (if necessary) is ensured by TZÚS Prague, OS 1020.

## DISTRIBUTOR:

LASSELSBERGER, s.r.o., Adelova 2549/1, 320 00 Pilsen – Jižní Předměstí

#### VALIDITY:

Since 1 March 2015

We reserve the right to make any changes that are the result of technical progress. This issue cancels and supersedes all previous issues.