

# Technical data sheet

|                                   |                                    |
|-----------------------------------|------------------------------------|
| Product: <b>GARJD561</b>          | Serie: <b>Mano</b>                 |
| Color: <b>beige</b>               | Norm: <b>EN 14411:annex H, B1b</b> |
| Nominal size: <b>10x30 cm</b>     | Declaration: <b>G 23 01</b>        |
| Declared size: <b>298x98x8 mm</b> | Group of goods: <b>GD</b>          |
|                                   | Product type: <b>compact tile</b>  |
| Surface: <b>relief glossy</b>     |                                    |

| Technical characteristics                | Norm                  | EN 14411:annex H<br>B1b                     | LB/RAKO                            |
|------------------------------------------|-----------------------|---------------------------------------------|------------------------------------|
| Tolerance - Length/width                 | ISO 10545-2           | ± 0,6%                                      | ± 0,4%                             |
| Tolerance - Thickness                    | ISO 10545-2           | ± 5%                                        | ± 5%                               |
| Tolerance - Straightness                 | ISO 10545-2           | ± 0,5%                                      | ± 0,25%                            |
| Tolerance - Rectangularity               | ISO 10545-2           | ± 0,5%                                      | ± 0,3%                             |
| Tolerance - Surface flatness             | ISO 10545-2           | ± 0,5%                                      | ± 0,25%                            |
| Surface quality                          | ISO 10545-2           | Min. 95%                                    | Min. 95%                           |
| Water absorption                         | ISO 10545-3           | 0,5% < E # 3%,ind.ma                        | E < 2,5%                           |
| Breaking strength                        | ISO 10545-4           | >= 7,5 mm min. 1300 N<br>< 7,5 mm min. 700N | >=700 N                            |
| Modulus of rupture                       | ISO 10545-4           | Min. 35 N/mm2<br>Ind.min. 32 N/mm2          | Min. 35 N/mm2<br>Ind.min. 32 N/mm2 |
| Resistance to deep abrasion (UGL)        | ISO 10545-6           | Not required                                | Not tested                         |
| Resistance to surface abrasion (GL)      | ISO 10545-7           | Declared value                              |                                    |
| Coefficient of linear thermal expansion  | ISO 10545-8           | Declared value                              | Max. 0,000008 / K                  |
| Thermal shock resistance                 | ISO 10545-9           | Required                                    | Resistant                          |
| Crazing resistance                       | ISO 10545-11          | Required                                    | Resistant                          |
| Freeze-thaw resistance                   | ISO 10545-12          | Declared value                              | resistant                          |
| Durability for: internal use             | EN 14411              | Pass                                        | Pass                               |
| Slipperiness (bare feet)                 | EN 16165              | Declared value                              | uncategorized                      |
| Slipperiness (shod feet)                 | EN 16165              | Declared value                              | uncategorized                      |
| Coefficient of friction (dry)            | EN 16165              | Declared value                              | >=0,3                              |
| Coefficient of friction (wet)            | EN 16165              | Declared value                              | >=0,3                              |
| Discharge volume                         | DIN 51 097            | Declared value                              | not relevant                       |
| Bond strength/adhesion-cem. adhesives    | EN 12004:2007+A1:2012 | Declared value                              | >=1,0 N/mm2                        |
| Bond strength/adhesion-dispers. adhesiv. | EN 12004:2007+A1:2012 | Declared value                              | NPD*                               |
| Bond strength/adhesion-rea. resin adhes. | EN 12004:2007+A1:2012 | Declared value                              | NPD*                               |
| Bond strength/adhesion-mortar            | EN 12004:2007+A1:2012 | Declared value                              | NPD*                               |
| Moisture expansion                       | ISO 10545-10          | Declared value                              | 0,2 mm/m                           |
| Light reflectance value LRV              | ISO 10545-18          | Not required                                |                                    |
| Impact resistance: Coef. of restit.      | ISO 10545-5           | Declared value                              | Min. 0,6                           |
| Reaction to fire                         | NO TESTING 96/603 EHS | Class A1-A1FL                               | Class A1-A1FL                      |
| Tactility                                | CEN/TS 15209          | Declare<br>surface description              | not relevant                       |
| Resistance to staining                   | ISO 10545-14          | Min. 3                                      | Min. 3                             |
| Resistance to low conc.of acids/alkalis  | ISO 10545-13          | Declared value                              | A                                  |
| Resistance to high conc.of acids/alkalis | ISO 10545-13          | Declared value                              | B                                  |
| Resist. to house. chem. and swim. pool   | ISO 10545-13          | Min. B                                      | A                                  |
| Release of dang.subs.: Cadmium (GL)      | ISO 10545-15          | Declared value                              | NPD*                               |
| Release of dang.subs.: Lead (GL)         | ISO 10545-15          | Declared value                              | NPD*                               |
| Surface hardness according to Mohs       | EN 101                | Not required                                | Min. 5                             |
| The reference life (RSL)                 | ISO 14 025/EN 15804   | 50 years                                    | 50 years                           |
| Assessment of nat.radionuclide content   | CZ IMP.422/2016       | Max. index 1,0                              | Max. index 1,0                     |

\* No Performance Determined – NPD